

**RSFR-H****3:1****RSFR-H - Heat shrinkable polyolefin tubing**UL approved  
UL category YDPU2/8  
File E203950

<b>Item description:</b>	Halogen Free - Flame Retardant – Heat Shrinkable Tube
<b>Item Code:</b>	RSFR-H
<b>UL File:</b>	E203950–Cat. UL YDPU2/8 (Tubing, Extruded Insulation – Component) VW-1 600Volt (colors recognized: all colors except clear)

This specification defines technical requirement, testing method, testing rules and packing of heat shrinkable tubes.

**Applications**

RSFR-H heat shrinkable tubing is used as connection, protection, identification... of electrical cables. Also used as electrical insulation, mechanical protection in general; as a protection of metallic rods, tubes, antenna...

**Standard**

Standard for Extruded Electrical Tubing UL224

**Description**

RSFR-H tube is extruded, radiate to make it cross linked, then expanded and cooled at the required size. It contains flame retardant components without halogens and without heavy metal so satisfying flame retardant and environmental standards. RSFR-H is Rohs and Reach SVHC compliant.

**Technical requirements:**

Temperature ranges: -55°C +125°C  
Shrinking ratio: 3  
:1  
Shrinking temperature: starts at 70°C and shrunk totally at 125°C  
Longitudinal shrinking: ≤ 5% (±5%)

**Colors:**

Black is standard color. On request: Red, Blue, Yellow, Green, White. Other colors such as purple, grey, brown can be made according to customer's requirements.



Via Abitazione, 5/1 Loc. Monteveglio  
40050 Valsamoggia (BO) Italy  
Tel. 0039 051 832485 Fax 051 832601  
e-mail: [info@isolcavi.it](mailto:info@isolcavi.it) [www.isolcavi.com](http://www.isolcavi.com)



Technical specifications		Testing method	Requirement
Physical	Tensile strenght /MPa	GB/T1040	≥10.4
	Elongation %	GB/T1040	≥200
	Tensile strenght after aging /MPa	UL224	≥7.3
	Elongation after aging %	UL224	≥100
	Heat Resistance	UL224	No cracking
	Cold bend	UL224	No cracking
Electrical	Dielectric withstand (600 V)	UL224	≥2500V
	Dielectric strenght KV/mm	GB/T1408	≥15
	Volume resistance Ω cm	GB/T1410	≥10 <sup>14</sup>
Chemical	Anti corrosion	UL224	Pass
	Copper stability	UL224	Pass
	Flammability	UL224	VW-1 (except clear)

Dimensional values			
As supplied mm.	After recovery mm.		Packing mt.
	Diam.mm.	Thickness mm.	
1.5	≤ 0.5	0.45 ± 0.10	200
3.0	≤ 1.0	0.55 ± 0.10	200
4.5	≤ 1.5	0.60 ± 0.10	100
6.0	≤ 2.0	0.65 ± 0.10	100
9.0	≤ 3.0	0.75 ± 0.15	100
12.0	≤ 4.0	0.75 ± 0.15	100
18.0	≤ 6.0	0.85 ± 0.15	100
24.0	≤ 8.0	1.00 ± 0.20	50
39.0	≤ 13.0	1.50 ± 0.20	50
50.0	≤ 16.0	2.50 ± 0.20	25

It must be stored in a dry place, inside plastic bags, away from direct sunlight, weathering, chemical materials, direct heat sources or fire. Storage time is 12 months.

The values given above are believed to be accurate and given as a matter of information only. As usage conditions are beyond our control we suggest the customer to confirm values and product compatibility prior to its use. We don't guarantee nor accept any responsibility for any particular usage.



Via Abitazione, 5/1 Loc. Monteveglio  
40050 Valsamoggia (BO) Italy  
Tel. 0039 051 832485 Fax 051 832601  
e-mail: [info@isolcavi.it](mailto:info@isolcavi.it) [www.isolcavi.com](http://www.isolcavi.com)

